

EPOX IN 25

Reinforcing Purpose, Epoxy Based Injection System

Description

EPOX IN 25, is an epoxy based, two component, without filler, injection system that fills and holds together hole and cracks of construction elements with high diffusion property.

Fields of Application

- On damaged concrete columns, beams, walls and other structural elements,
- To reinforce construction with filling the static cracks of concrete, stone and brick.

Features and Benefits

- High diffusion ability due to the low viscosity
- Provides excellent adhesion with filling the holes on system without losing volume.
- Can be injected into humid concrete.

Technical Data

Content	Component A : Epoxy Resin Component B : Epoxy Hardener
Color	Transparent
Mixture Density	1,0 – 1,1 g/cm ³
Solid Content	100%
Viscosity	200 – 300 MPa.s
Compressive Strength	>65 N/mm ² (7 days)
Flexural Strength	>25 N/mm ² (7 days)
Adhesion on Concrete	>2 N/mm ² (7 days)
Flash Point	> +62°C
Application Temperature	+10°C to +35°C
Pot Life	25 minutes
Drying Time	
<i>Re-coating</i>	<i>18-24 hours</i>
<i>Full curing</i>	<i>7 days</i>
HS Code	3907.30

EPOX IN 25

Reinforcing Purpose, Epoxy Based Injection System

Application Procedure

Preparation of Substrate

Cracks, which became apparent on the surface should be opened with a handheld grinder in a reverse cone shape with the dimensions of 5-10 mm in width and 10-12 mm in depth. Dust and other contaminants must be removed with pressurized air.

Application Method

Packers help **EPOX IN 25** epoxy resin to penetrate into the cracks throughout the concrete. Packers are inserted into the holes with a drill. **EPOX IN 25** is injected into the packers through the nozzles. Usually drill packers are used. Injection operation is done with special pumps (with single or double heads). **EPOX IN 25** should be used with a single headed pump, if applied quickly. Otherwise a double headed pump is necessary. The operation pressure shouldn't exceed 5 bars. Usually when injection starts through one packer it continues till **EPOX IN 25** comes out of from the closest packer or packers. **EPOX IN 25** (epoxy resin) doesn't move on with the help of pump pressure, it moves with own pressure throughout capillary veins.

Consumption

Depends on usage area. Recommended application thickness is min. 0,2 mm / max. 5,0 mm.

Packaging

A component: 6,67 kg + B component: 3,33 kg = 10 kg set

Shelf Life

18 months in original, unopened package.

Storage

Store in dry area between +5°C and +35°C. Protect from heat, freezing and direct sunlight.

Cleanup Information

Clean tools and equipment with industrial type solvents immediately after use. Dried material can only be removed mechanically.

EPOX IN 25

Reinforcing Purpose, Epoxy Based Injection System

Cautions / Limitations

- It may be harmful with skin contact.
- Do not apply in freezing conditions or during precipitation.
- Protect applied materials from rain, freezing, foot traffic and continuous high humidity until completely dry.
- Do not use when air and surface temperatures are below +10°C and above +35°C.
- Avoid heavy traffic for 24 hours.

Health and Safety

Warning! Cause eye and skin irritation. If eye or skin contact, get immediate medical attention. If swallowed, do not induce vomiting. Call a physician or poison control center. Never give anything by mouth to an unconscious person.

Wash hands thoroughly after handling. Wear protective clothing, gloves, eye and face protection. Do not eat, drink or smoke when using this product. Take off contaminated clothing and wash it before reuse. Dispose of unused, contents, container and other contaminated wastes in accordance with local, state, federal and provincial regulations.

Keep container closed when not in use. Keep out of the reach of children.

Limited Warranty: This product is subject to a written limited warranty which can be obtained free of charge from BAUMERK Company. Please contact with technical service department for further information and support.